



## SNK-2242(Aromatic Polyurethane Acrylate)

### Basic Information

- Place of Origin: Wuhan, Hubei, China
- Brand Name: Meilun Materials
- Model Number: SNK-2242
- Minimum Order Quantity: 20kg
- Packaging Details: 20kg/barrel, 200kg/barrel
- Supply Ability: 50T/month



SNK-2242

### Product Specification

- Highlight: UV resin with excellent bonding performance,  
Aliphatic polyurethane,  
Aliphatic polyurethane acrylate

## Product Description

UV adhesive resin(Aromatic polyurethane acrylate)SNK-2242

### Product Description:

Used for bonding between glass, and between glass and aluminum alloys. It is also used in flexographic printing plate making, LCD display bonding, UV water glue, feel paints, potting compounds, and PET adhesion.

### Typical performance characteristics:

- 1:Adhesive for glass/metal bonding,Low odor,Strong adhesive strength,Good elasticity,Excellent resistance to yellowing,Tear resistance.
- 2:Specifications:Number of functional groups: 2,Curing energy: 500-1000mJ/cm<sup>2</sup>,Soluble in ketones, esters, and aromatic hydrocarbon solvents.
- 3:Processes: Adhesive application, silk-screen printing, roller coating, spray coating, etc.Soluble in conventional UV monomers, resins, etc.
- 4:High-performance flexible plate making, PET in-mold printing.
- 5: Can be used in other formulations to improve adhesion.

### Technical Parameters:

#### SNK-2242

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	Mps.s/40°C	25000-45000
2	Solid content	%	≥98
3	Exterior		transparent viscous substance
4	AV value	mgKOH/g	≤2
5	NCO	mgKOH/g	≤2
6	color number	Gardner,25°C	<1
7	Tear strength	MPa	4
8	glass transition temperature	TG	-30
9	molecular weight	Mw	10000-20000
10	Moisture content	25°C/%	< 0.1
11	Polymerization inhibitor	ppm	< 400
12	Elongation	%	800-1000

### Storage and validity period:

- 1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage.
- 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.
- 3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

### Package

200 kilograms/iron drum  
20 kilograms/iron drum  
200 kilograms/plastic drum  
20 kilograms/plastic drum



Wuhan Meilun New Materials Co., Ltd



+8618062439876



hu1150563785@gmail.com



[melonmaterials.com](http://melonmaterials.com)

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan