

SNK-2228 (Aliphatic Polyurethane Acrylate)

Basic Information

- Place of Origin:
- n: Wuhan, Hubei, China
- Brand Name:
- Meilun Materials SNK-2228
- Model Number: SN
- Minimum Order Quantity:
- Packaging Details:
- Supply Ability:
- 20kg
- : 20kg/barrel, 200kg/barrel 50T/month



Product Specification

Highlight:

coating crystal clear resin, UV crystal clear resin, liquid plastic resin SNK-2228

Our Product Introduction

UV Plastic Coating Resin(Aliphatic polyurethane acrylate)SNK-2228

Product Description:

Main Applications: This product is suitable for bonding PET, glass, acrylic, and stainless steel. It can be used for bonding glass to glass, as well as glass to aluminum alloy. Additionally, it is used in coatings for optical fibers, UV adhesives, nail polish, edge sealing, encapsulation, pressure-sensitive adhesives, and more.

Processes: include adhesive applications, screen printing, roller coating, spraying, etc. It is soluble in conventional UV monomers, resins, and other solvents. It's a versatile solution for various bonding and coating applications across different substrates and industries.

Typical performance characteristics

1:Excellent temperature resistance, yellowing resistance, water resistance, and tear resistance. 2:Number of functional groups: 2, curing energy: 500-1000 mJ/cm², can be cured under UV/UV-LED. 3:Molecular weight (Mw) = 1500-3000, soluble in ketones, esters, and aromatic solvents.

Technical Parameters:

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	mpa.s/40°C	40000-65000
2	Solid content	%	≥98
3	Exterior		Light yellow, viscous liquid
4	color number	Gardner,25°C	<1
5	Polymerization inhibitor	ppm	< 400

Storage and validity period:

1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage. 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.

3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

Package:

200 kilograms/iron drum 20 kilograms/iron drum 200 kilograms/plastic drum

Wuhan Meilun New Materials Co., Ltd
 +8618062439876
 hu1150563785@gmail.com
 melonmaterials.com

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan