



SNK-2269A (Polyurethane Acrylate)

Basic Information

- Place of Origin: Wuhan, Hubei, China
- Brand Name: Meilun Materials
- Model Number: SNK-2269A
- Minimum Order Quantity: 20kg
- Packaging Details: 20kg/barrel, 200kg/barrel
- Payment Terms: L/C, T/T
- Supply Ability: 50T/month



SNK-2269A

Product Specification

- Highlight: 50000mpa.s/40°C uv ink,
65000mpa.s/40°C uv ink SNK-2269A,
Poly urethane acrylate SNK-2269A

Product Description

UV Graphic Arts Inks(Polyurethane acrylate) SNK-2269A

Product Description:

Main applications: Suitable for UV-curable inks and UV offset printing ink systems.

Processes: screen printing, offset printing, etc. Miscible with conventional UV monomers and resins.

Typical performance characteristics:

- ⊗ Excellent adhesion, good temperature and chemical resistance, excellent yellowing resistance, good film strength.
- ⊗ Number of functional groups: 2, curing energy: 500-800 mJ/cm², soluble in ketone, ester, and aromatic solvents.
- ⊗ Molecular weight Mw = 3000-5000.

Technical Parameters:

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	mpa.s/40°C	5000-6500
2	Solid content	%	≥98
3	Exterior		Slightly yellow viscous
4	color number	Gardner,25°C	<1
5	AV	mgKOH/g	≤15
6	NCO	mgKOH/g	≤2
7	Polymerization inhibitor	ppm	< 400

Storage and validity period:

- 1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage.
- 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.
- 3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

Package

200 kilograms/iron drum
 20 kilograms/iron drum
 200 kilograms/plastic drum
 20 kilograms/plastic drum



Wuhan Meilun New Materials Co., Ltd



+8618062439876



hu1150563785@gmail.com



melonmaterials.com

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan