



SNK-9203(Polyester Acrylate)

Basic Information

- Place of Origin: Wuhan, Hubei, China
- Brand Name: Meilun Materials
- Model Number: SNK-9203
- Minimum Order Quantity: 20kg
- Packaging Details: 20kg/barrel, 200kg/barrel
- Payment Terms: L/C, T/T
- Supply Ability: 50T/month



SNK-9203

Product Specification

- Highlight: 13000mpa.s/25°C metal epoxy,
18000mpa.s/25°C high heat metal epoxy,
liquid metal epoxy Golden transparent

Product Description

UV Metal Adhesion Resin(Polyester acrylate) SNK-9203

Product Description:

Main applications: This product is suitable for glass, metal, and etching ink (alkaline wash) applications. It can perform alkaline washing with a 5% NaOH solution at 30°C for no more than 5 minutes. It can also be used for cover plate ink, as well as for bonding between glass or between glass and aluminum alloy.

Process: Screen printing, roller coating, spraying, adhesives, etc. It is miscible with conventional UV monomers and resins.

Typical performance characteristics:

Excellent adhesion (3M tape test shows no peeling), good water resistance, high cost-performance ratio, excellent yellowing resistance, resistant to cutting fluid for ≥ 0.5 hours, hardness $\geq 1H$.

Alkaline washing speed and water resistance can be adjusted with trifunctional or higher monomers or resins. UV curing can be followed by infrared heating to enhance adhesion.

Number of functional groups: bifunctional, curing energy: 500-800 mJ/cm², soluble in ketones, esters, and aromatic solvents.

Molecular weight (Mw): 1500-2000.

Technical Parameters:

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	mpa.s/25°C	13000-18000
2	Solid content	%	≥ 98
3	Exterior		Golden transparent
4	color number	Gardner,25°C	< 2
5	AV	mgKOH/g	≤ 15
6	NCO	mgKOH/g	≤ 2
7	Polymerization inhibitor	ppm	< 400

Storage and validity period:

1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage.

2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.

3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

Package

200 kilograms/iron drum

20 kilograms/iron drum

200 kilograms/plastic drum

20 kilograms/plastic drum



Wuhan Meilun New Materials Co., Ltd



+8618062439876



hu1150563785@gmail.com



melonmaterials.com

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan