


# SNK-2269A (Polyurethane Acrylate) Metal Bonding Ероху

# **Basic Information**

- Place of Origin:
- Wuhan, Hubei, China Meilun Materials
- Brand Name:
- SNK-2269A Model Number: 20kg
- Minimum Order Quantity:
- Packaging Details:
- Payment Terms:
- Supply Ability:
- 20kg/barrel, 200kg/barrel L/C, T/T
- 50T/month



# **Product Specification**

• Highlight:

curable metal bonding epoxy, offset printing metal bonding epoxy, UV Polyurethane Acrylate

Our Product Introduction

## **Product Description**

UV Graphic Arts Inks(Polyurethane acrylate) SNK-2269A

#### Product Description:

Main applications: Suitable for UV-curable inks and UV offset printing ink systems.

Processes: screen printing, offset printing, etc. Miscible with conventional UV monomers and resins.

#### Typical performance characteristics:

Excellent adhesion, good temperature and chemical resistance, excellent yellowing resistance, good film strength.
Number of functional groups: 2, curing energy: 500-800 mJ/cm<sup>2</sup>, soluble in ketone, ester, and aromatic solvents.
Molecular weight Mw = 3000-5000.

## **Technical Parameters:**

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	mpa.s/40°C	5000-6500
2	Solid content	%	≥98
3	Exterior		Slightly yellow viscous
4	color number	Gardner,25°C	<1
5	AV	mgKOH/g	≤15
6	NCO	mgKOH/g	≤2
7	Polymerization inhibitor	ppm	< 400

## Storage and validity period:

1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage. 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.

3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

#### Package

200 kilograms/iron drum 20 kilograms/iron drum 200 kilograms/plastic drum 20 kilograms/plastic drum

