



## SNK-2117 ( Polyurethane Acrylate) Metal Epoxy

Our Product Introduction

### Basic Information

- Place of Origin: Wuhan, Hubei, China
- Brand Name: Meilun Materials
- Model Number: SNK-2117
- Minimum Order Quantity: 20kg
- Packaging Details: 20kg/barrel, 200kg/barrel
- Supply Ability: 50T/month



SNK-2117

### Product Specification

- Highlight:
  - snk-2117 uv resin high adhesion Polyurethane Acrylate
  - , snk-2117 uv resin metal epoxy Polyurethane Acrylate
  - , 98% solid content epoxy glue for metal

for more products please visit us on [melonmaterials.com](http://melonmaterials.com)

## Product Description

High Adhesion UV Plastic Coating Resin Polyurethane Acrylate SNK-2117

### Product Description:

Main applications: This is a high-adhesion resin, providing adhesion in various formulations and in white wood applications, as well as offering curing properties.

Processes: screen printing, roller coating, spraying, adhesive applications, etc. It can be mixed with conventional UV monomers and resins. This product can be directly adjusted with monomers to achieve desired performance and can be used in other formulations to improve adhesion.

### Typical performance characteristics

- 1: Excellent yellowing resistance, excellent water resistance, good adhesion, quick surface drying under LED.
- 2: Number of functional groups: 6, Curing energy: 300-500 mJ/cm<sup>2</sup>, can be cured with both UV and UV-LED.
- 3: Molecular weight (Mw): 1500-3000, soluble in ketones, esters, and aromatic solvents.

### Technical Parameters:

serial number	Technical parameter items	unit	Technical parameters
1	viscosity	mpa.s/25°C	40000-60000
2	Solid content	%	≥98
3	Exterior		Slightly yellow viscous
4	color number	Gardner, 25°C	<1
5	AV	mgKOH/g	≤3
6	NCO	mgKOH/g	≤3
7	Polymerization inhibitor	ppm	< 400

### Storage and validity period:

- 1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage.
- 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.
- 3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

### Package:

200 kilograms/iron drum  
20 kilograms/iron drum  
200 kilograms/plastic drum



Wuhan Meilun New Materials Co., Ltd



+8618062439876



hu1150563785@gmail.com



[melonmaterials.com](http://melonmaterials.com)

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan