

# SNK-2203 (Polyurethane Acrylate)

# **Basic Information**

- Place of Origin:
- rigin: Wuhan, Hubei, China
- Brand Name:
- Meilun Materials SNK-2203
- Model Number: SN
- Minimum Order Quantity:
- Packaging Details:
- Supply Ability:
- y: 20kg
- 20kg/barrel, 200kg/barrel 50T/month

® SNK-2203

## **Product Specification**

Highlight:

80Mps.s/25°C clear coating epoxy resin, 150Mps.s/25°C clear coating epoxy resin, OPP PET epoxy clear coat

Our Product Introduction

#### **Product Description:**

Main applications: Used for substrates that are difficult to adhere to: OPP, PET, bottom coating varnish, metal screen printing, 3D inkjet printing, PET adhesion.

Processes: screen printing, roller coating, spraying, adhesives, etc. Compatible with conventional UV monomers and resins. This product can be directly adjusted with monomers to achieve desired performance and can be used in other formulations to enhance adhesion.

## Typical performance characteristics:

Excellent yellowing resistance, exceptional adhesion, low viscosity, and the cured resin is relatively soft. Number of functional groups: 2, curing energy:  $300-500 \text{ mJ/cm}^2$ , can be cured with UV/UV-LED. Molecular weight (Mw) = 1500-3000, soluble in ketones, esters, and aromatic solvents.

## **Technical Parameters:**

| serial number | Technical parameter items   | unit         | Technical parameters            |
|---------------|-----------------------------|--------------|---------------------------------|
| 1             | viscosity                   | Mps.s/25°C   | 80-150                          |
| 2             | Solid content               | %            | ≥98                             |
| 3             | Exterior                    |              | Light yellow,<br>viscous liquid |
| 4             | color number                | Gardner,25°C | <1                              |
| 5             | AV                          | mgKOH/g      | ≤15                             |
| 6             | NCO                         | mgKOH/g      | ≤2                              |
| 7             | Polymerization<br>inhibitor | ppm          | < 400                           |

## Storage and validity period:

1: This product should be stored in a cool, well-ventilated room, and strictly protected from light exposure for stable storage. 2: Keep the resin away from heat sources and store it in a dark place to prevent potential hazards or affecting the stability of resin storage.

3: When stored at room temperature, it remains stable for six months. After use, please tightly seal the container to avoid exposure to light sources and gelation.

#### Package:

200 kilograms/iron drum 20 kilograms/iron drum 200 kilograms/plastic drum

Wuhan Meilun New Materials Co., Ltd

+8618062439876

ø

hu1150563785@gmail.com 😥 melonmaterials.com

Room 1206-1207, Building 8, Country Garden Yunxi Office, No. 20 Gaokeyuan West Road, Jiufeng Street, East Lake New Technology Development Zone, Wuhan